



Application/Uses

- Bags and sacks
- Agricultural films
- Trash bags and liners
- Co-extruded structures

Product Description

Westlake LF9220AA is a hexene LLDPE with excellent physical properties and heat sealing characteristics, which allow for down-gauging and blending with other materials. Typical applications include stretch films, heavy duty bags and sacks, agricultural films, and trash bags & liners. This Kosher compliant material is available with various slip and antiblock levels.

Typical Physical Properties

| <u>Property</u> | | <u>Test Method</u> | <u>Typical Value, Units</u> |
|---------------------|----|--------------------|--|
| Melt Index | | D 1238 | 1.0 g/10 min |
| Density* | | D 1505 | 919 kg/m ³ (0.919 g/cm ³) |
| Haze* | | D 1003 | 15.0 % |
| Dart Impact | | D 1709 | 220 g/mil |
| Tensile Break | MD | D 882 | 5,900 psi |
| | TD | D 882 | 4,100 psi |
| Ultimate Elongation | MD | D 882 | 670 % |
| | TD | D 882 | 900 % |
| 1% Secant Modulus | MD | D 882 | 30,000 psi |
| | TD | D 882 | 36,000 psi |

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

Kosher Compliant. Test specimens for blown film: nominal thickness 1.0 mils fabricated at 2.5:1 BUR.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Blown melt temperatures of 400° F – 420° F are recommended for Westlake Chemical LF9220AA.

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION
2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-800-545-9577