

# Linear Low Density Polyethylene

**XLL4**

## PRODUCT DESCRIPTION

LLDPE butene resin for general packaging application.

## APPLICATIONS

Product used for general packaging, including agriculture film.

## TYPICAL PROPERTIES

Properties		Typical Value	Unit	Test Method
Melt Flow Index (190°C/2.16 kg)		1.0 - 1.1	g/10 min	ASTM D1238
Density		0.918 - 0.919	g/cm <sup>3</sup>	ASTM D1505
Tensile Strength at Break	MD	35 - 37	Mpa	ASTM D882
	TD	23 - 25		
Elongation at Break	MD	490 - 510	%	ASTM D882
	TD	740 - 760		
Haze		15.0	%	ASTM D1003
Dart Drop Impact Strength, F50		115 - 125	g	ASTM D1709A

## ADDITIVE

Slip	AVAILABLE
------	-----------

**DISCLAIMER:** THIS TECHNICAL DATA SHEET SHOWS THE TYPICAL PROPERTIES AND THE DATA SHOWN ARE NOT TO BE CONSTRUED AS SPECIFICATIONS. THE DOCUMENT IS DESIGNED TO PROVIDE USERS GENERAL INFORMATION AND DOES NOT CONSTITUTE ANY WARRANTY OR QUALITY SPECIFICATION, EITHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. USERS SHALL DETERMINE WHETHER THE PRODUCT IS SUITABLE FOR THEIR USE AND CAN BE USED SAFELY AND LEGALLY.