





PP

►HY300

Homo PP for stretched tapes

Description

HY300 is an isotactic homo PP grade for extrusion application. It is designed for the production of films which can be converted into stretched tape, and injection molded housewares.

Characteristics

- ► Excellent processability & mechanical properties
- ► High stretchability & productivity

Applications

▶ Woven bags, Stretched band, PP filament, Fishing net, rod

Physical Properties

| Typical Properties | Method (ASTM) | Unit | HY300 |
|----------------------------|------------------|--------------------|--------|
| Melt flow index | D1238 | g/10min | 3.9 |
| Density | D1505 | g/cm ³ | 0.91 |
| Tensile strength at yield | D638 | kg/cm ² | 380 |
| Elongation at break | D638 | % | 500 |
| Flexural modulus | D790 | kg/cm ² | 14,500 |
| Izod impact strength 23 °C | D256 | kgcm/cm | 4 |
| Rockwell hardness | D785 | R-scale | 100 |
| Heat distortion temp. | D648 | $^{\circ}$ | 110 |

^{*} Data shown above are representative values for reference purposes only, and not to be construed as specifications.

^{*} Data performed by or on behalf of Hanwha Total



Food Contact Application

- ▶ There may be some limitation to apply Hanwha Total HY300 to the food packaging. Thus, the verification on the suitability is necessary.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

Contacts

▶ Product Information & Technical Services

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do, Korea, 31900

TEL: 82-41-660-6190 FAX: 82-41-660-6189

Disclaimer

This document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.