Isplen® Polypropylene

Chemicals

Technical data sheet





ISPLEN® PB 180 G2M

ISPLEN® PB 180 G2M is a high fluidity heterophasic copolymer characterised by its excellent flow properties and by its good balance of mechanical properties: impact strength and stiffness. It is particularly suitable for injection moulding applications of thin walled articles. The material also shows very low tendency to warp and it is used in goods where dimensional stability is important.

TYPICAL APPLICATIONS

The particular characteristics of ISPLEN® PB 180 G2M permit a grade intended for use in applications where good proccesability is appreciated in addition with good mechanical properties:

- Domestic and leisure furniture.
- Square boxes and round storage containers for consumer appliances.
- Trays and containers for cold storage of foodstuffs: ice creams, fresh vegetables, fruit processed...
- Industrial components: toys, sports, leisure, automotive, storage organizers, packaging...

Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

| PROPERTIES | VALUE | UNIT | TEST METHOD |
|--------------------------------------|-------|-------------------|-------------|
| General | | | |
| Melt Flow Rate (230 °C; 2.16 kg) | 20 | g/10 min | ISO 1133 |
| Density | 905 | kg/m ³ | ISO 1183 |
| | | | |
| Mechanical | | | |
| Flexural Modulus | 1250 | MPa | ISO 178 |
| Charpy Impact Strength Notched 23 °C | 6 | kJ/m ² | ISO 179 |
| | | | |
| Thermal | | | |
| Heat Deflection Temperature 0.45MPa | 88 | °C | ISO 75 |
| | | | |
| Others | | | |
| Shore Hardness | 62 | D Scale | ISO 868 |

ISPLEN® PB 180 G2M complies with the European Directives regarding materials intended for contact with foodstuffs. For further information, please contact our Technical Service and Development Laboratory or our Customer Care Service.

STORAGE

ISPLEN® PB 180 G2M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes which may have a negative influence on the processability and the properties of the transformed product.

November 2013