



January, 2013

# KOPELEN JM-375

## PP BLOCK COPOLYMER

#### **General Information**

### **Description**

JM-375 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-375 shows a high melt flow, controlled rheology and has good balance of strength, impact resistance, and processability.

### **Applications**

- General supplies & Industrial supplies
- Automotive compound base resin

	Physical Properties <sup>1</sup>				
Physical	Test Method		Nominal Va		
Melt Flow Index	ASTM D1238	45	g/10min		
Density	ASTM D792	0.90	g/cm <sup>3</sup>		
Mechanical					-
Tensile Stress (Yield)	ASTM D638	260	kgf/cm <sup>2</sup>	25	MPa
Tensile Strain (Break)	ASTM D638	>50	%	>50	%
Flexural Modulus	ASTM D790	15,000	kgf/cm <sup>2</sup>	1,470	MPa
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	7.5	kgf-cm/cm	74	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	3.5	kgf-cm/cm	34	J/m
Thermal	. 9				
Heat Deflection Temperature (4.6kgf/cm²)	ASTM D648	125	°C		
Additional Properties					
Flammability	UL94	-			

<sup>&</sup>lt;sup>1</sup> Physical Properties : these are not to be construed as specifications



January, 2013

# KOPELEN JM-375

## PP BLOCK COPOLYMER

### **General Information**

### Description

JM-375 is high impact block copolymer which has high ethylene-propylene rubber content. This grade is designed to be processed in conventional Injection molding equipment. JM-375 shows a high melt flow, controlled rheology and has good balance of strength, impact resistance, and processability.

### Applications

- General supplies & Industrial supplies
- Automotive compound base resin

	Physical Properties <sup>1</sup>				
Physical	Test Method		Nominal Values		
Melt Flow Index	ISO 1133	45	g/10min		
Density	ISO 1183	0.90	g/cm <sup>3</sup>		
Mechanical					
Tensile Stress (Yield)	ISO 527-1	250	kgf/cm <sup>2</sup>	<b>25</b> MPa	
Tensile Strain (Break)	ISO 527-1	<100	% <10	00 %	
Flexural Modulus	ISO 178	13,000	kgf/cm <sup>2</sup> 1,2	<b>70</b> MPa	
Impact		/ 🛪			
Notched Izod Impact Strength (23℃)	ISO 180	7	kgf·cm/cm	<b>39</b> J/m	
Notched Izod Impact Strength (-10℃)	ISO 180	3	kgf·cm/cm	29 J/m	
Thermal	. 7				
Heat Deflection Temperature (4.6kgf/cm²)	ISO 75-1	105	°C		
Additional Properties					
Flammability	UL94	-			

<sup>&</sup>lt;sup>1</sup> Physical Properties : these are not to be construed as specifications