

**HUZUR**

www.huzurplastik.com

info@huzurplastik.com

+90 212 444 14 97

سابك
sabik
SABIC® PP 575P**PP homopolymer for Injection moulding****Description:**

This grade combines a high stiffness with moderate impact strength. It is suitable for production of complex articles with long flow paths and thin walls. Typical applications are closures and garden furniture.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site
<http://www.SABIC-europe.com>

Typical values

Revision 20060227

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg at 230 °C and 5 kg	g/10 min g/10 min kg/m ³	10.5 38 905	ISO 1133
Density			ISO 1183
Mechanical properties			
Tensile test stress at yield stress at break strain at break	MPa MPa %	43 34 600	ISO 527
Flexural test Flexural modulus	MPa	1800	ASTM D 790
Izod impact notched at 23 °C	kJ/m ²	2.0	ISO 180/4A
Charpy impact notched at 23 °C	kJ/m ²	1.5	ISO 179
Hardness Shore D	-	72	ISO 868
Thermal properties			
Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)	°C °C	54 98	ISO 75/A ISO 75/B
Vicat softening temperature at 10 N (VST/A) at 50 N (VST/B)	°C °C	152 90	ISO 306/A ISO 306/B

All information supplied by or on behalf of any of the SABIC Europe companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC Europe company assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to any of the SABIC Europe companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.