



SABIC® Vestolen P 9421

PP random copolymer for Pipe extrusion

Description:

This random copolymer has a high molecular weight with special designed properties required for high demanding pressure pipes. It is highly heat stabilised and especially formulated for extraction resistance. This grade with long service life is used for the manufacturing of cold and hot water pipes and fittings for transport of drinking water. It complies with German regulations for materials in contact with water intended for human consumption (BGA requirements and KTW recommendations).

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

Typical values

Revision 20090604

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Colour	-	Natural	-
Melt flow rate (MFR) at 190 °C and 5 kg	g/10 min	0.50	ISO 1133
at 230 °C and 2.16 kg	g/10 min	0.30	
Density	kg/m ³	898	ISO 1183
Mechanical properties			
Tensile test stress at yield	MPa	27	ISO 527
stress at break	MPa	32	
strain at break	%	>50	
Flexural test Flexural modulus	MPa	900	ASTM D 790
Izod impact notched at 23 °C	kJ/m ²	15	ISO 180/4A
at 0 °C	kJ/m ²	-	
at -20 °C	kJ/m ²	-	
Charpy impact notched at 23 °C	kJ/m ²	25	ISO 179
at 0 °C	kJ/m ²	-	
at -20 °C	kJ/m ²	-	
Charpy impact unnotched at 23 °C	kJ/m ²	>60	ISO 179
Thermal properties			
Vicat softening temperature at 10 N (VST/A)	°C	130	ISO 306/A
at 50 N (VST/B)	°C	61	ISO 306/B



SABIC® Vestolen P 9421

PP random copolymer for Pipe extrusion

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.