

POLYPROPYLENE

Y101



www.huzurplastik.com
info@huzurplastik.com
+90 212 444 14 97

Homopolymer Polypropylene for injection molding application

Description

Y101 is a homopolymer polypropylene intended for injection molding applications. Molded part made from this resin exhibit high stiffness, good heat resistance and good flow characteristic.

Applications

- General purpose
- Housewares

Resin Properties	Unit	Test Method	Typical Value
MFR (230°C/2.16Kg)	g/10min	ASTM D1238	15
Density	g/cm ³	ASTM D792 Method A	0.9
Mechanical Properties*			
Tensile Strength at Yield	MPa	ASTM D638	34
Tensile Strength at Break	MPa	ASTM D638	28
Flexural Modulus	MPa	ASTM D790	1700
Izod Impact, Notched 23 °C	kJ/m ²	ASTM D256	2.0
Rockwell Hardness-R		ASTM D785	105
Thermal Properties*			
Vicat Softening Temperature @10N	°C	ASTM D1525	158
Heat Deflection 0.45MPa	°C	ASTM D648	116
Other			
Shrinkage MD/TD	%	SUMIKA	1.2/1.2
Flammability		UL94	HB

*Test specimen preparation Method: Pursuant to ASTM D4101

Processing conditions: Recommended melt temperature: 160 – 240 °C

Storage and handling: Y101 should be stored in a dry cool place with adequate ventilation and protected from UV-light at temperature below 50 °C

Food Contact Compliance and other Regulations: Please contact Petro Rabigh.