



## TCI Sanmar Chemicals S.A.E

### Polyvinyl Chloride PVC K-6701

K-6701 is a medium molecular weight Polyvinyl Chloride homopolymer suspension resin produced by suspension process

Parameter	Test Procedure	Unit	Typical Value
K-Value	INEOS PM01	Number	67 ± 1
Partical size < 63 µm (230 mesh)	ASTM D 1921-06	%	5.0 max
Partical size > 250 µm (60 mesh)	ASTM D 1921-06	%	5.0 max
Bulk Density	ASTM D 1895-03	g/ml	0.52 ± 0.03
Dark Resin (in 100 gms)	INEOS PM06	Number	25 max
Heat Loss	ASTM D 3030-06	%	0.3 max

#### Application

Rigid Pipes-Portable water pipes, SWR Pipes, Drainage Pipes  
Rigid duct, Conduit & Trunking for telecommunication & Cable

#### Packaging

1.125 MT Jumbo woven sacks bag with inner liners